

PAROC InVent 60 N3



Short Description

Stone wool slab with black glass fibre felt facing.

Application

Ventilation attenuation slab.

Technical Properties

Nominal Density

60 kg/m³

Surface temperature of the facing must not exceed 80°C (temperature restriction determined in accordance with heat resistance adhesive).

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Width x Length

600x1200 mm

Other Dimensions

Other dimensions available on request.

Thickness

50-100 mm

Packaging

Plastic packs on pallet

Fire Properties

Reaction to Fire, Euroclass

A1

In accordance with

EN 13501-1

Thermal Properties

Thermal Conductivity in 10 °C, λ_{10} 0,037 W/mK

Moisture Properties

Short Term Water Absorption (Declared), WS, (W_p)

≤ 1 kg/m²

In accordance with

EN 1609

Designation Code

MW-EN 14303-T5-WS1



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2012